

Description	Limit	Test Methods
Density at 25°C	1.01-1.06	ASTM D-70
Penetration Rate at 25°C	100-120	ASTM D-5
Softening Point °C	42-49	ASTM D-36
Ductility at 25 °C (cm), Min	100	ASTM D-113
Flash Point °C, Min	250	ASTM D-92
Solubility in Trichloroethylene %wt., Min	99.0	ASTM D-4
Loss on Heating %, Max	0.2	ASTM D-6
Spot Test	Negative	A.A.S.H.O.T.102