

Description	Limit	Test Methods
Density at 25°C	1.00-1.05	ASTM D-70
Penetration Rate at 25°C	100-150	ASTM D-5
Softening Point °C	39-47	ASTM D-36
Ductility at 25 °C (cm), Min	100	ASTM D-113
Flash Point °C, Min	218	ASTM D-92
Solubility in Trichloroethylene %wt., Min	99.0	ASTM D-4
Loss on Heating %, Max	0.5	ASTM D-6
Spot Test	Negative	A.A.S.H.O.T.102