

Bitumen 30/40	Test method	Unit	Specifications
Specific Gravity @ 25°C	ASTM D-70	Kg/cm ³	1.01-1.06
Penetration @ 25°C	ASTM D-5	mm/10	30-40
Softening Point °C	ASTM D-36	°C	55-63
Ductility @25 °C	ASTM D-113	cm	100 Min
Loss on Heating (wt.) %	ASTM D-6	Wt. %	0.2 Max
Drop in Penetration after Heating %	ASTM D-5 D-6	%	20 Max
Flash Point °C	ASTM D-92	°C	250 Min
Solubility in CS ₂ (wt.) %	ASTM D-4	Wt. %	99.5 Min
Spot Test	A.A.S.H.O. T102	-	Negative