

Description	Limit	Test Methods
Density at 25°C	1.01-1.06	ASTM D-7
Penetration Rate at 25°C	30-40	ASTM D-5
Softening Point °C	55-63	ASTM D-36
Ductility at 25 °C (cm) - Min	100	ASTM D-113
Flash Point °C - Min	250	ASTM D-92
Solubility in Disulfide %wt.	99.5	ASTM D-4
Spot Test	Negative	A.A.S.H.O.T.102
Weight Loss by Heating %wt., Max	0.2	ASTM D-6
Penetration Loss by Heating % , Max	20	ASTM D-5 D-6