

Description	Limit	Test Methods
Density at 25°C	1.01-1.06	ASTM D70
Penetration Rate at 25°C	40-60	EN 1426
Softening Point °C	48-56	EN 1427
Ductility at 25 °C (cm), Min	100	ASTM D113
Flash Point °C, Min	230	EN 22592
Solubility in Trichloroethylene or Xylene %wt., Min	99	ASTM D2042
Change in Mass %, Max	0.2	EN 12607-1
Retained Penetration 25°C, 100g, 5s (% of original) %, Min	50	EN 1426