

Description	Limit	Test Methods
Density at 25°C	1.01-1.06	ASTM D70
Penetration Rate at 25°C	60-70	ASTM D5
Softening Point °C	49-56	ASTM D36
Ductility at 25 °C (cm), Min	100	ASTM D113
Flash Point °C, Min	250	ASTM D92
Solubility in Disulfide %wt.	99.5	ASTM D2042
Spot Test	Negative	A.A.S.H.O.T.102
Weight Loss by Heating %Wt., Max	0.2	ASTM D6